

Cold-In-Place (CIP) Recycling

HMA Milling (Kornhill Road – 2011)



Adding Binder, Placing, and Compacting



Additional Hot Mix Asphalt (HMA) lifts over the CIP (Golden Road 2017)



- **30 year Design Life.** V62 with heavy truck traffic constructed in 1993.
- **Best Option.** Failing layer below the seal coats and failing edges on existing roads.
- **Eliminates reflective cracking.**
- **Longer Process.** Expect road closures 2 to 3 times longer than a more traditional HMA reconstruction.

